



AAROGREEN™ ARPP200 Series

TECHNICAL DATA SHEET

ARPP250-NOL-N PP BLEND Color Sorted Natural
(FDA NOL)

Properties	Test Method	Units	Typical Value
Physical			
Specific Gravity	ASTM D792	g/cm ³	0.920
Mold Shrinkage	ASTM D955	in/in	0.020
Mechanical			
Flexural Modulus	ASTM D790	psi	200,000
Tensile Strength @ Yield	ASTM D638	psi	3,700
Izod Impact @ 73°F (Notched)	ASTM D256	ft-lb/in	1.8
Thermal			
Melt Flow Rate	ASTM D1238 (230°C/2.16 kg)	g/10 min	20
Deflection Temperature	ASTM D648 (@ 66 psi)	°F	185

DESCRIPTION: A polypropylene resin blend made with 100% recycled content including 30% PCR featuring a combination of good flow characteristics and strength for all general purpose molding and extrusion applications.

- 100% Total Recycled Content (30% PCR)
- GreenCircle™ Certified
- FDA Letter #PNC2231

The information and recommendations in this publication are, to the best of our knowledge, reliable. Suggestions concerning uses or applications are only the opinion of Aaron Ind. Corp. and users should perform their own tests to determine the suitability of these products for their own purposes. However, because of numerous factors affecting results, Aaron Ind. Corp. MAKES NO WARRANTY OF ANY KIND, EXPRESS OR IMPLIED, INCLUDING THOSE OF MANUFACTURING AND FITNESS FOR PURPOSE.



- Suitable for Food Contact FDA Conditions of Use B through G

The information and recommendations in this publication are, to the best of our knowledge, reliable. Suggestions concerning uses or applications are only the opinion of Aaron Ind. Corp. and users should perform their own tests to determine the suitability of these products for their own purposes. However, because of numerous factors affecting results, Aaron Ind. Corp. MAKES NO WARRANTY OF ANY KIND, EXPRESS OR IMPLIED, INCLUDING THOSE OF MANUFACTURING AND FITNESS FOR PURPOSE.

20 MOHAWK DRIVE P.O. BOX 607 LEOMINSTER, MA 01453 • TEL: 800.915.6159 • FAX: 978.537.7360
e-mail: info@aaroninc.com web: www.aaroninc.com
